

## **GENERAL COATING SPECIFICATION FOR NEDOX® NH-1**

DESCRIPTION: INFUSED POLYMER ELECTROLESS NICKEL PLATING

COATING NAME:

COATING HARDNESS:

COATING THICKNESS:

TEMP OPERATING RANGE:

NEDOX NH-1

42 – 50 Rc

0.0003 – 0.0015"

-250F TO 500F

SALT SPRAY RESULTS: ~ 600 HOURS (ASTM B117)

EQUILIBRIUM WEAR RATES: 61 - 86 mg (mg/10,000 cycles ASTM D4060) COEFFICIENT OF FRICTION: 0.181 Static; 0.237 Kinetic (ASTM D1894)

FDA COMPLIANT: No

Data based on average of multiple samples. Results will vary and are application dependent.

