

GENERAL COATING SPECIFICATION FOR TUFRAM® R66LT

DESCRIPTION:	INFUSED POLYMER ANODIC COATING FOR CORROSIVE ENVIRONMENTS (pH 2-13)
COATING NAME:	TUFRAM R66LT
COATING HARDNESS:	42 – 50 Rc
COATING THICKNESS:	0.002 – 0.003” (includes anodic and polymer buildup)
TEMP OPERATING RANGE:	-360F TO 302F

**Data based on average of multiple samples.
Results will vary and are application dependent.**

