

GENERAL COATING SPECIFICATION FOR TUFAM® SLK

DESCRIPTION:	INFUSED POLYMER ANODIC COATING
COATING NAME:	TUFAM SLK
COATING HARDNESS:	42 – 50 Rc
COATING THICKNESS:	0.0015 – 0.0025” (includes anodic and polymer buildup)
TEMP OPERATING RANGE:	-360F TO 500F
FDA COMPLIANT:	Yes

**Data based on average of multiple samples.
Results will vary and are application dependent.**

